

Attorney Docket No: 1155-0241P
Application No. 10/046,738
Page 2

(B) a thermoplastic elastomer composition in an amount of 1 to 95 parts by weight, said thermoplastic elastomer composition being obtained by dynamically heat treating a crystalline polyolefin resin (a) and an olefin copolymer rubber (b) in the presence of a crosslinking agent,

the total of said components (A) and (B) being 100 parts by weight,

wherein the ethylene/ α -olefin copolymer (A) has:

(i) a Shore A hardness of 40 to 95 measured according to JIS K 6253,

(ii) a melt flow rate MFR_{2.16} of 1.0 to 100 g/10 min measured according to ASTM D 1238 at a load of 2.16 kg at 190°C, and

(iii) a density of 855 to 900 kg/m³ measured according to ASTM D 1505,

and

the thermoplastic elastomer composition (B) has:

(i) a gel content of 30 to 100 %, and

(ii) a Shore A hardness of 40 to 95 measured according to JIS K 6253.

Attorney Docket No: 1155-0241P
Application No. 10/046,738
Page 3

Claim 2 (Amended) The injection molding soft resin composition as claimed in claim 1, having a Shore A hardness of 40 to 95 measured according to JIS K 6253 and a melt flow rate MFR_{2.16} of 1.0 to 100 g/10 min measured according to ASTM D 1238 under a load of 2.16 kg at 190°C.

Claim 3 (Amended) The injection molding soft resin composition as claimed in claim 1, wherein the ethylene/ α -olefin copolymer (A) has:

(iv) a molecular weight distribution (Mw/Mn), as determined by gel permeation chromatography (GPC), of 1 to 3, and

(v) a ratio (MFR₁₀/MFR_{2.16}) of a melt flow rate MFR₁₀ g/10 min measured according to ASTM D 1238 under a load of 10 kg at 190°C to the MFR_{2.16} (g/10 min) ranging from 5 to 20.

Claim 4 (Amended) The injection molding soft resin composition as claimed in claim 1, wherein the ethylene/ α -olefin copolymer (A) is a mixture of at least two different ethylene/ α -olefin copolymers (A).

Attorney Docket No: 1155-0241P
Application No. 10/046,738
Page 4

Claim 6 (Amended) The injection molded article as claimed in claim 5, which has been painted on the surface.

Claim 7 (Amended) The injection molded article as claimed in claim 5, which has been provided with a color finish by painting, said color finish being provided by coating the surface of the injection molded article with a primer comprising a styrene elastomer resin having been graft polymerized with a monomer having an α,β -monoethylenically unsaturated group and then painting the surface.

Claim 8 (Amended) The injection molded article as claimed in claim 5, which has been provided with a color finish by painting, said color finish being provided by coating the surface of the injection molded article with a composition comprising a styrene elastomer resin having been graft polymerized with a monomer having an α, β -monoethylenically unsaturated group and a photopolymerization initiator, subjecting the coated surface to UV treatment and then painting the surface.

Attorney Docket No: 1155-0241P
Application No. 10/046,738
Page 5

Claim 9 (Amended) A toy comprising the injection molded article of claim 5.

Claim 10 (Amended) A daily use miscellaneous article comprising the injection molded article of claim 5.

Add the following new claims:

- - Claim 11 A toy comprising the injection molded article of claim 6.

Claim 12 A toy comprising the injection molded article of claim 7.

Claim 13 A toy comprising the injection molded article of claim 8.

Claim 14 A daily use miscellaneous article comprising the injection molded article of claim 6.

Claim 15 A daily use miscellaneous article comprising the injection molded article of claim 7.